

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

2021年4月

試験者

吉田 竜哉



試験測定結果			規格 (JIS A 5001)											
ふるい目	試料番号	F-2.5	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5			
ふるいを通るものの質量百分率 (%)	106		106	100										
	75		75	85~100	100									
	63		63	0~15	85~100									
	53		53			100								
	37.5		37.5		0~15	85~100	100							
	31.5		31.5			0~15	85~100							
	26.5		26.5					100						
	19.0		19.0				0~15	85~100	100					
	13.2		13.2					0~15	85~100	100				
	9.5		9.5											
	4.75	100.0	4.75							0~15	85~100	100		
	2.36	94.2	2.36								0~25	85~100		
	1.18	67.0	1.18								0~5			
	0.6	45.9	0.6										25~55	
0.3	32.6	0.3											15~40	
0.15	16.0	0.15											7~28	
0.075	9.2	0.075											0~20	
微粒分量(%)		JIS A 1103	1.0(1.5)%以下										—	
単位容積質量(t/m ³)	1.697	JIS A 1104	—										—	
実積率(%)	64.8		—										—	
表乾密度(g/cm ³)	2.638	JIS A 1110	2.45以上										—	
吸水率(%)	0.80	JIS A 1109	3.0%以下										—	
すりへり減量(%)		JIS A 1121	30%以下										—	
安定性(%)	4.5	JIS A 1122	12%以下										—	
軟石量(%)		JIS A 1126	5%以下										—	
骨材の形状(%)		舗装試験法便覧	10%以下										—	
塑性指数	NP	JIS A 1205	NP										—	