

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

2020年4月

試験者

吉田 竜哉



試験測定結果			規格 (JIS A 5001)											
ふるい目	試料番号	F-2.5	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5			
ふるいを通るものの質量百分率 (%)	106		106	100										
	75		75	85~100	100									
	63		63	0~15	85~100									
	53		53			100								
	37.5		37.5		0~15	85~100	100							
	31.5		31.5			0~15	85~100							
	26.5		26.5						100					
	19.0		19.0					0~15	85~100	100				
	13.2		13.2						0~15	85~100	100			
	9.5		9.5											
	4.75	100.0	4.75							0~15	85~100	100		
	2.36	93.1	2.36								0~25	85~100		
	JIS A 1102	1.18	69.5	1.18							0~5			
		0.6	42.3	0.6									25~55	
	0.3	28.8	0.3										15~40	
	0.15	14.1	0.15										7~28	
	0.075	9.7	0.075										0~20	
微粒分量(%)			JIS A 1103	1.0(1.5)%以下										—
単位容積質量(t/m <sup>3</sup> )	1.686		JIS A 1104	—										
実積率(%)	64.7			—										
表乾密度(g/cm <sup>3</sup> )	2.631		JIS A 1110	2.45以上										
吸水率(%)	0.93		JIS A 1109	3.0%以下										
すりへり減量(%)			JIS A 1121	30%以下										—
安定性(%)	3.5		JIS A 1122	12%以下										—
軟石量(%)			JIS A 1126	5%以下										—
骨材の形状(%)			舗装試験法便覧	10%以下										—
塑性指数	NP		JIS A 1205	NP										