

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

2020年4月

試験者

吉田 竜哉



		試験測定結果		規格 (JIS A 5001)									
ふるい目		試料番号	S-40	S-30	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5
ふるいを通るものの質量百分率 (%)	106				106	100							
	75				75	85~100	100						
	63				63	0~15	85~100						
	53		100.0		53			100					
	37.5		95.1	100.0	37.5		0~15	85~100	100				
	31.5		6.3	96.7	31.5			0~15	85~100				
	26.5		0.0	46.5	26.5					100			
	19.0			5.1	19.0				0~15	85~100	100		
	13.2			0.0	13.2					0~15	85~100	100	
	9.5				9.5								
	4.75				4.75						0~15	85~100	100
	2.36				2.36							0~25	85~100
	JIS A 1102	1.18			1.18							0~5	
		0.6			0.6								25~55
		0.3			0.3								15~40
	0.15			0.15								7~28	
	0.075			0.075								0~20	
微粒分量(%)					JIS A 1103	1.0(1.5)%以下						—	
単位容積質量(t/m ³)			1.519	1.520	JIS A 1104	—						—	
実積率(%)			58.3	58.8		—						—	
表乾密度(g/cm ³)			2.629	2.613	JIS A 1110	2.45以上						—	
吸水率(%)			0.97	1.04	JIS A 1109	3.0%以下						—	
すりへり減量(%)			14.9	14.6	JIS A 1121	30%以下						—	
安定性(%)					JIS A 1122	12%以下						—	
軟石量(%)					JIS A 1126	5%以下						—	
骨材の形状(%)			0.0	0.0	舗装試験法便覧	10%以下						—	