

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

2020年4月

試験者

吉田 竜哉



| ふるい目 | | 試験測定結果 | | | 規格 (JIS A 5001) | | | | | | | | | | | | | |
|----------------------------|------------|--------|-------|------------|-----------------|----------|--------|--------|--------|--------|------|------|--------|--------|-----|------|-------|--|
| | | 試料番号 | S-20 | S-13 | S-5 | ふるい目(mm) | S-80 | S-60 | S-40 | S-30 | S-20 | S-13 | S-5 | F2.5 | | | | |
| ふるいを通るものの質量百分率 (%) | 106 | | | | 106 | 100 | | | | | | | | | | | | |
| | 75 | | | | 75 | 85~100 | 100 | | | | | | | | | | | |
| | 63 | | | | 63 | 0~15 | 85~100 | | | | | | | | | | | |
| | 53 | | | | 53 | | | 100 | | | | | | | | | | |
| | 37.5 | | | | 37.5 | | 0~15 | 85~100 | 100 | | | | | | | | | |
| | 31.5 | | | | 31.5 | | | 0~15 | 85~100 | | | | | | | | | |
| | 26.5 | 100.0 | | | 26.5 | | | | | 100 | | | | | | | | |
| | 19.0 | 95.1 | 100.0 | | 19.0 | | | | 0~15 | 85~100 | 100 | | | | | | | |
| | 13.2 | 8.7 | 93.7 | | 13.2 | | | | 0~15 | 85~100 | | 100 | | | | | | |
| | 9.5 | 0.0 | 52.9 | 100.0 | 9.5 | | | | | | | | | | | | | |
| | 4.75 | | 2.9 | 93.0 | 4.75 | | | | | | | 0~15 | 85~100 | | 100 | | | |
| | 2.36 | | 0.0 | 5.3 | 2.36 | | | | | | | | 0~25 | 85~100 | | | | |
| | JIS A 1102 | 1.18 | | 1.3 | 1.18 | | | | | | | | | 0~5 | | | | |
| | | 0.6 | | 0.0 | 0.6 | | | | | | | | | | | | 25~55 | |
| | | 0.3 | | | 0.3 | | | | | | | | | | | | 15~40 | |
| | 0.15 | | | 0.15 | | | | | | | | | | | | 7~28 | | |
| | 0.075 | | | 0.075 | | | | | | | | | | | | 0~20 | | |
| 微粒分量(%) | | | | JIS A 1103 | 1.0(1.5)%以下 | | | | | | | | | | — | | | |
| 単位容積質量(g/cm ³) | 1.517 | 1.511 | 1.492 | JIS A 1104 | — | | | | | | | | | | — | | | |
| 実積率(%) | 58.0 | 57.6 | 57.2 | JIS A 1110 | — | | | | | | | | | | — | | | |
| 表乾密度(g/cm ³) | 2.643 | 2.643 | 2.639 | JIS A 1110 | 2.45以上 | | | | | | | | | | — | | | |
| 吸水率(%) | 1.12 | 0.75 | 1.09 | JIS A 1109 | 3.0%以下 | | | | | | | | | | — | | | |
| すりへり減量(%) | 12.8 | 12.7 | 17.6 | JIS A 1121 | 30%以下 | | | | | | | | | | — | | | |
| 安定性(%) | 4.4 | 3.6 | 3.5 | JIS A 1122 | 12%以下 | | | | | | | | | | — | | | |
| 軟石量(%) | | | | JIS A 1126 | 5%以下 | | | | | | | | | | — | | | |
| 骨材の形状(%) | 0.4 | 0.4 | | 舗装試験法便覧 | 10%以下 | | | | | | | | | | — | | | |
| | | | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | | |