

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

30年 4月

試験者

吉田 竜哉

		試験測定結果			規格 (JIS A 5001)									
ふるい目		試料番号	S-20	S-13	S-5	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5
ふるいを通るものの質量百分率 (%)	106					106	100							
	75					75	85~100	100						
	63					63	0~15	85~100						
	53					53			100					
	37.5					37.5		0~15	85~100	100				
	31.5					31.5			0~15	85~100				
	26.5	100.0				26.5					100			
	19.0	91.8	100.0			19.0				0~15	85~100	100		
	13.2	9.9	90.2			13.2					0~15	85~100	100	
	9.5	0.0	47.9	100.0		9.5								
	4.75		1.5	92.1		4.75						0~15	85~100	100
	2.36		0.0	7.1		2.36							0~25	85~100
	JIS A 1102	1.18		1.7		1.18							0~5	
		0.6		0.0		0.6								25~55
		0.3				0.3								15~40
	0.15				0.15								7~28	
	0.075				0.075								0~20	
微粒分量(%)					JIS A 1103	1.0(1.5)%以下								—
単位容積質量(g/cm ³)		1.517	1.513	1.505	JIS A 1104	—								—
実績率(%)		58.0	58.1	58.0		—								—
表乾密度(g/cm ³)		2.633	2.628	2.619	JIS A 1110	2.45以上								—
吸水率(%)		0.72	0.86	0.97	JIS A 1109	3.0%以下								—
すりへり減量(%)		12.1	11.8	17.3	JIS A 1121	30%以下								—
安定性(%)		4.7	4.1	2.7	JIS A 1122	12%以下								—
軟石量(%)					JIS A 1126	5%以下								—
骨材の形状(%)		0.3	0.1		舗装試験法便覧	10%以下								—