

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

31年 4月

試験者

吉田 竜哉



試験測定結果				規格 (JIS A 5001)										
ふるい目	試料番号	S-20	S-13	S-5	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5	
ふるいを通るものの質量百分率 (%)	106				106	100								
	75				75	85~100	100							
	63				63	0~15	85~100							
	53				53			100						
	37.5				37.5		0~15	85~100	100					
	31.5				31.5			0~15	85~100					
	26.5	100.0			26.5					100				
	19.0	93.6	100.0		19.0				0~15	85~100	100			
	13.2	8.3	92.5		13.2					0~15	85~100	100		
	9.5	0.0	49.6	100.0	9.5									
	4.75		1.5	92.4	4.75						0~15	85~100	100	
	2.36		0.0	6.7	2.36							0~25	85~100	
	JIS A 1102	1.18		1.2	1.18							0~5		
		0.6		0.0	0.6								25~55	
		0.3			0.3								15~40	
	0.15			0.15								7~28		
	0.075			0.075								0~20		
微粒分量(%)					JIS A 1103	1.0(1.5)%以下							—	
単位容積質量(g/cm <sup>3</sup> )	1.520	1.521	1.507					JIS A 1104	—					
実績率(%)	58.2	57.6	57.2					JIS A 1104	—					
表乾密度(g/cm <sup>3</sup> )	2.641	2.659	2.651					JIS A 1110	2.45以上					
吸水率(%)	1.17	0.68	0.67					JIS A 1109	3.0%以下					
すりへり減量(%)	12.3	11.8	14.5					JIS A 1121	30%以下					
安定性(%)	4.4	3.6	3.3					JIS A 1122	12%以下					
軟石量(%)									JIS A 1126	5%以下				
骨材の形状(%)	0.3	0.2					舗装試験法便覧				10%以下		—	