

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

2023年4月

試験者

吉田 竜哉



|                            |            | 試験測定結果 |       |            | 規格 (JIS A 5001) |        |        |        |        |        |        |        |        |   |
|----------------------------|------------|--------|-------|------------|-----------------|--------|--------|--------|--------|--------|--------|--------|--------|---|
| ふるい目                       | 試料番号       | S-20   | S-13  | S-5        | ふるい目(mm)        | S-80   | S-60   | S-40   | S-30   | S-20   | S-13   | S-5    | F2.5   |   |
| ふるいを通るものの質量百分率 (%)         | 106        |        |       |            | 106             | 100    |        |        |        |        |        |        |        |   |
|                            | 75         |        |       |            | 75              | 85~100 | 100    |        |        |        |        |        |        |   |
|                            | 63         |        |       |            | 63              | 0~15   | 85~100 |        |        |        |        |        |        |   |
|                            | 53         |        |       |            | 53              |        |        | 100    |        |        |        |        |        |   |
|                            | 37.5       |        |       |            | 37.5            |        | 0~15   | 85~100 | 100    |        |        |        |        |   |
|                            | 31.5       |        |       |            | 31.5            |        |        | 0~15   | 85~100 |        |        |        |        |   |
|                            | 26.5       | 100.0  |       |            | 26.5            |        |        |        |        | 100    |        |        |        |   |
|                            | 19.0       | 92.6   | 100.0 |            | 19.0            |        |        |        | 0~15   | 85~100 | 100    |        |        |   |
|                            | 13.2       | 6.3    | 90.8  |            | 13.2            |        |        |        |        | 0~15   | 85~100 | 100    |        |   |
|                            | 9.5        | 0.0    | 49.7  | 100.0      | 9.5             |        |        |        |        |        |        |        |        |   |
|                            | 4.75       |        | 1.4   | 91.5       | 4.75            |        |        |        |        |        | 0~15   | 85~100 | 100    |   |
|                            | 2.36       |        | 0.0   | 5.7        | 2.36            |        |        |        |        |        |        | 0~25   | 85~100 |   |
|                            | JIS A 1102 | 1.18   |       | 1.3        | 1.18            |        |        |        |        |        |        | 0~5    |        |   |
|                            |            | 0.6    |       | 0.0        | 0.6             |        |        |        |        |        |        |        | 25~55  |   |
|                            |            | 0.3    |       |            | 0.3             |        |        |        |        |        |        |        | 15~40  |   |
|                            | 0.15       |        |       | 0.15       |                 |        |        |        |        |        |        | 7~28   |        |   |
|                            | 0.075      |        |       | 0.075      |                 |        |        |        |        |        |        | 0~20   |        |   |
| 微粒分量(%)                    |            | 0.72   |       | JIS A 1103 | 1.0(1.5)%以下     |        |        |        |        |        |        |        | —      |   |
| 単位容積質量(g/cm <sup>3</sup> ) | 1.527      | 1.532  | 1.505 | JIS A 1104 | —               |        |        |        |        |        |        |        |        |   |
| 実積率(%)                     | 58.4       | 58.3   | 57.5  |            | —               |        |        |        |        |        |        |        |        |   |
| 表乾密度(g/cm <sup>3</sup> )   | 2.638      | 2.645  | 2.642 | JIS A 1110 | 2.45以上          |        |        |        |        |        |        |        |        |   |
| 吸水率(%)                     | 0.90       | 0.75   | 0.89  | JIS A 1109 | 3.0%以下          |        |        |        |        |        |        |        |        |   |
| すりへり減量(%)                  | 12.2       | 12.0   | 15.9  | JIS A 1121 | 30%以下           |        |        |        |        |        |        |        |        | — |
| 安定性(%)                     | 4.1        | 3.6    | 3.5   | JIS A 1122 | 12%以下           |        |        |        |        |        |        |        |        | — |
| 軟石量(%)                     |            |        |       | JIS A 1126 | 5%以下            |        |        |        |        |        |        |        |        | — |
| 骨材の形状(%)                   | 0.3        | 0.3    |       | 舗装試験法便覧    | 10%以下           |        |        |        |        |        |        |        |        | — |
| 粘土塊(%)                     |            | 0.03   |       | JIS A 1137 | 0.25%以下         |        |        |        |        |        |        |        |        |   |
| 粒形判定実積率(%)                 |            | 57.4   |       | JIS A 1104 | —               |        |        |        |        |        |        |        |        |   |