

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

2024年4月

試験者

吉田 竜哉

		試験測定結果			規格 (JIS A 5001)									
ふるい目	試料番号	S-20	S-13	S-5	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5	
ふるいを通るものの質量百分率 (%)	106				106	100								
	75				75	85~100	100							
	63				63	0~15	85~100							
	53				53			100						
	37.5				37.5		0~15	85~100	100					
	31.5				31.5			0~15	85~100					
	26.5	100.0			26.5					100				
	19.0	91.2	100.0		19.0				0~15	85~100	100			
	13.2	6.0	91.5		13.2					0~15	85~100	100		
	9.5	0.0	49.0	100.0	9.5									
	4.75		1.3	93.1	4.75						0~15	85~100	100	
	2.36		0.0	6.4	2.36							0~25	85~100	
	1.18			1.0	1.18							0~5		
	0.6			0.0	0.6								25~55	
	0.3				0.3								15~40	
0.15				0.15									7~28	
0.075				0.075									0~20	
微粒分量(%)			0.68	JIS A 1103		1.0(1.5)%以下							—	
単位容積質量(g/cm ³)	1.519	1.541	1.501	JIS A 1104		—								
実積率(%)	58.0	58.6	57.2			—								
表乾密度(g/cm ³)	2.643	2.648	2.645	JIS A 1110		2.45以上								
吸水率(%)	0.85	0.71	0.86	JIS A 1109		3.0%以下								
すりへり減量(%)	12.4	11.9	16.0	JIS A 1121		30%以下							—	
安定性(%)	4.0	3.5	3.7	JIS A 1122		12%以下							—	
軟石量(%)				JIS A 1126		5%以下							—	
骨材の形状(%)	0.2	0.3		舗装試験法便覧		10%以下							—	
粘土塊(%)		0.04		JIS A 1137		0.25%以下								
粒形判定実積率(%)		58.3		JIS A 1104		—								