

株式会社 丸高商事
 調査名・産地 岐阜県郡上市大和町大間見字天野洞
 報告年月日 2025年4月

試験者 吉田 竜哉

ふるい目		試験測定結果			規格 (JIS A 5001)												
		S-20	S-13	S-5	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5				
ふるいを通るものの質量百分率 (%)	106				106	100											
	75				75	85~100	100										
	63				63	0~15	85~100										
	53				53			100									
	37.5				37.5		0~15	85~100	100								
	31.5				31.5			0~15	85~100								
	26.5	100.0			26.5					100							
	19.0	91.6	100.0		19.0				0~15	85~100	100						
	13.2	5.5	89.6		13.2					0~15	85~100	100					
	9.5	0.0	49.8	100.0	9.5												
	4.75		1.2	91.8	4.75							0~15	85~100	100			
	2.36		0.0	6.5	2.36								0~25	85~100			
	JIS A 1102	1.18		1.1	1.18									0~5			
		0.6		0.0	0.6											25~55	
		0.3			0.3											15~40	
	0.15			0.15											7~28		
	0.075			0.075											0~20		
微粒分量(%)		0.72		JIS A 1103	1.0(1.5)%以下										—		
単位容積質量(g/cm ³)	1.522	1.559	1.493	JIS A 1104	—										—		
実積率(%)	57.9	59.5	57.1		—										—		
表乾密度(g/cm ³)	2.648	2.642	2.636	JIS A 1110	2.45以上										—		
吸水率(%)	0.82	0.76	0.90	JIS A 1109	3.0%以下										—		
すりへり減量(%)	12.2	11.3	16.7	JIS A 1121	30%以下										—		
安定性(%)	4.1	3.7	3.3	JIS A 1122	12%以下										—		
軟石量(%)				JIS A 1126	5%以下										—		
骨材の形状(%)	0.3	0.2		舗装試験法便覧	10%以下										—		
粘土塊(%)		0.03		JIS A 1137	0.25%以下										—		
粒形判定実積率(%)		58.9		JIS A 1104	—										—		