

株式会社 丸高商事

調査名・産地

岐阜県郡上市大和町大間見字天野洞

報告年月日

2026年4月

試験者

吉田 竜哉

		試験測定結果			規格 (JIS A 5001)									
ふるい目		試料番号	S-20	S-13	S-5	ふるい目(mm)	S-80	S-60	S-40	S-30	S-20	S-13	S-5	F2.5
ふるいを通るものの質量百分率 (%)	106					106	100							
	75					75	85~100	100						
	63					63	0~15	85~100						
	53					53			100					
	37.5					37.5		0~15	85~100	100				
	31.5					31.5			0~15	85~100				
	26.5	100.0				26.5					100			
	19.0	91.0	100.0			19.0				0~15	85~100	100		
	13.2	5.7	90.2			13.2					0~15	85~100	100	
	9.5	0.0	49.3	100.0		9.5								
	4.75		1.5	92.4		4.75						0~15	85~100	100
	2.36		0.0	6.1		2.36							0~25	85~100
	1.18			1.5		1.18							0~5	
	0.6			0.0		0.6								25~55
	0.3					0.3								15~40
0.15					0.15								7~28	
0.075					0.075								0~20	
微粒分量(%)			0.67		JIS A 1103	1.0(1.5)%以下			—					
単位容積質量(g/cm <sup>3</sup> )		1.516	1.550	1.497	JIS A 1104	—								
実積率(%)		57.6	59.0	57.2		—								
表乾密度(g/cm <sup>3</sup> )		2.652	2.645	2.640	JIS A 1110	2.45以上								
吸水率(%)		0.79	0.73	0.84	JIS A 1109	3.0%以下								
すりへり減量(%)		12.5	11.6	16.2	JIS A 1121	30%以下								
安定性(%)		3.8	3.3	3.5	JIS A 1122	12%以下								
軟石量(%)					JIS A 1126	5%以下								
骨材の形状(%)		0.2	0.2		舗装試験法便覧	10%以下								
粘土塊(%)			0.04		JIS A 1137	0.25%以下								
粒形判定実積率(%)			59.2		JIS A 1104	—								